

LANTHANIDE-BASED NANOPARTICLES FOR MULTIMODAL MOLECULAR IMAGING AND TARGETED ALPHA THERAPY

Purpose: To assess the in vitro retention of therapeutically relevant radionuclides such as in vivo α -generators Ra-223, Ac-225, and Th-227 in lanthanide phosphate (LnPO₄) and lanthanide vanadate (LnVO₄) core-shell nanoparticles (NPs) towards their promising application as multifunctional platforms in nanomedicine.

Method and Materials: LnPO₄ and LnVO₄ core-shell NPs doped with either Eu-156, a radionuclide “cocktail” of Sr-85, Sr-89, Eu-156, or in vivo α -generators Ra-223, Ac-225, and Th-227 were synthesized in aqueous media. In vitro retention of radionuclides was assessed by dialyzing the radioactive NPs suspensions against deionized water and quantifying the activity in dialysate aliquots over time using a high purity germanium detector. The crystal structure, morphology, colloidal stability, luminescence and magnetic properties of LnPO₄ and LnVO₄ core-shell NPs were evaluated.

Results: Partial retention of Eu-156 (~70–95%) and Sr-85 (>80%) was evidenced in LnPO₄ core NPs, while Th-227 and decay daughters were retained quantitatively (>99%) in LnPO₄ core-shell NPs. Gd_{0.8}Eu_{0.2}VO₄ and GdVO₄ core-shell NPs showed partial retention of Ra-223 (~75%), Ac-225 (75–95%), and Th-227 (>96%). Retention of decay daughters in LnVO₄ NPs was enhanced after deposition of nonradioactive shells. Adjusting the lanthanide concentration provided luminescence and magnetic properties for fluorescence and magnetic resonance imaging. Emission intensities were higher for LnVO₄ NPs with respect to LnPO₄, whereas no significant difference was observed in the magnetic susceptibility. GdVO₄ core NPs displayed enhancement of the signal intensity of T1-weighted images.

Conclusion: This work evidences the potential application of LnPO₄ and LnVO₄ core-shell NPs as platforms for multimodality molecular imaging and targeted alpha therapy. Partial retention of radionuclides may enhance the efficacy of treatment while minimizing the dose delivered to healthy organs. Radionuclide retention was influenced by the lanthanide concentration, the crystal structure, and the number of shells added.

Acknowledgments

This work was financed by the Virginia Commonwealth University (VCU) with the support of the Mechanical and Nuclear Engineering Department and NRC-HQ-84-14-FOA-002, Faculty Development Program in Radiation Detection and Health Physics at VCU. Work at ORNL was supported in part by (i) the U.S. Department of Energy Isotope Program within the Office of Nuclear Physics and (ii) an appointment to the Oak Ridge National Laboratory Nuclear Engineering Science Laboratory Synthesis Program, sponsored by the US Department of Energy and administered by the Oak Ridge Institute for Science and Education. We would like to thank the staff of Nuclear and Radiochemistry Group at ORNL for their help with radiochemistry and radioactivity measurements. The authors also wish to thank Dr. Joseph Turner from the Instrumentation Laboratory in the Department of Chemistry at VCU and the staff at the Nanomaterials Core Characterization Facility in the VCU College of Engineering.

Email Address

torogonzalezm@vcu.edu

Presentation Type

Contributed Oral

Primary author: Mr TORO-GONZALEZ, Miguel (Virginia Commonwealth University)

Co-authors: Dr ROJAS, Jessika V. (Assistant Professor, Virginia Commonwealth University); Dr MIRZADEH, Saed (Nuclear Security and Isotope Technology Division, Oak Ridge National Laboratory)

Presenter: Mr TORO-GONZALEZ, Miguel (Virginia Commonwealth University)

Track Classification: Targeting