Contribution ID: 13 Type: Contributed Oral

## Tracking the Progress of Nonuniform Deterioration in a Lithium-Ion Battery Using Bragg-Edge Imaging – an Application of the AISTANS Compact Neutron Source

Thursday, 27 February 2025 14:20 (20 minutes)

One of the challenges to overcome for commercial lithium-ion batteries (LIB) is suppression of power-storage degradation due to charge-discharge cycles. Some of the present authors (K. Kino and T. Fujiwara) and their collaborators previously reported nonuniform degradation of LIBs nondestructively and quantitatively by a Bragg-edge imaging experiment conducted at a large neutron facility, the Materials and Life Science Experimental Facility of the Japan Proton Accelerator Research Complex (J-PARC).[1] However, further understanding this process, especially clarifying the degradation progression, requires tracking the deterioration of an LIB cell over a long term by repeating Bragg-edge imaging after some charge-discharge cycles. Compact accelerator-driven neutron sources (CANS) are suitable for this research because of their flexible neutron-beam schedule and machine operation with a small number of researchers.

Therefore, we are conducting a long-term measurement of repeated Bragg-edge imaging of a commercial LIB cell for mobile phones after multiple charge-discharge cycles at AISTANS (Analytical facility for Industrial Science and Technology using Accelerator based Neutron Source) [2-4], which is located at AIST (National Institute of Advanced Industrial Science and Technology) Tsukuba in Japan. AISTANS can provide a thermal-cold pulsed neutron beam from a decoupled solid-methane moderator. Thanks to the optimization of AISTANS for Bragg-edge imaging from the most upstream (an electron accelerator) to the most downstream (a neutron detector), we succeeded in imaging three crystalline phases of a negative electrode (graphite, LiC12, and LiC6) in an area of approximately 50×50 mm2 for an initial fresh state. Currently, measurements after charge-discharge cycles are being conducted.

In this presentation, the latest result of tracking progress of nonuniform deterioration for a LIB cell by Braggedge imaging will be shown as an application of CANS.

## References

- [1] K. Kino et al., Appl. Phys. Express 15 (2022) 027005.
- [2] K. Kino et al., Eur. Phys. J. Plus (2022) 137:1260.
- [3] B.E. O'Rourke et al., Nuclear Inst. and Methods in Physics Research, B 464 (2020) 41–44.
- [4] K. Kino et al., Nuclear Inst. and Methods in Physics Research, A 927 (2019) 407-418.

## **Email Address**

Email Address

Presenter if not the submitter of this abstract

**Funding Agency** 

Abstract classification - track type

Applications

Primary authors: KINO, Koichi (National Institute of Advanced Industrial Science and Technology (AIST)); Dr

FUJIWARA, Takeshi (National Institute of Advanced Industrial Science and Technology (AIST)); Dr SHIBUYA, Tatsunori (National Institute of Advanced Industrial Science and Technology (AIST)); Dr O'ROURKE, Brian (National Institute of Advanced Industrial Science and Technology (AIST))

Presenter: KINO, Koichi (National Institute of Advanced Industrial Science and Technology (AIST))

**Session Classification:** Session 10